

SECTION 321400 - UNIT PAVING

PART 1 - GENERAL

1.1 SUMMARY

A. Section Includes:

1. Brick pavers.

1.2 ACTION SUBMITTALS

A. Product Data: For materials other than water and aggregates.

B. Samples: For each type of unit paver indicated

1. Joint materials involving color selection.
2. Exposed edge restraints involving color selection.

1.3 INFORMATIONAL SUBMITTALS

1.4 QUALITY ASSURANCE

A. Installer Qualifications: A qualified unit paving installer. Installer's personnel assigned to the Work shall have Concrete Paver Installer Certification from the Interlocking Concrete Pavement Institute (ICPI) with one of the following designations:

1. Commercial Paver Technician Designation.

1.5 FIELD CONDITIONS

A. Cold-Weather Protection: Do not use frozen materials or materials mixed or coated with ice or frost. Do not build on frozen subgrade or setting beds. Remove and replace unit paver work damaged by frost or freezing.

B. Weather Limitations for Bituminous Setting Bed: Install bituminous setting bed only when ambient temperature is above 40 deg F and when base is dry.

C. Weather Limitations for Mortar and Grout:

1. Cold-Weather Requirements: Comply with cold-weather construction requirements contained in TMS 602/ACI 530.1/ASCE 6.
2. Hot-Weather Requirements: Comply with hot-weather construction requirements contained in TMS 602/ACI 530.1/ASCE 6. Provide artificial shade and windbreaks and

use cooled materials as required. Do not apply mortar to substrates with temperatures of 100 deg F and higher.

PART 2 - PRODUCTS

2.1 BRICK PAVERS

- A. Brick Pavers, Light-Traffic Paving Brick: ASTM C902, Class SX , Type I Application PX . Provide brick without frogs or cores in surfaces exposed to view in the completed Work.
 - 1. Reference NCSU Facilities Preferred Products - Accessible via <https://facilities.ofa.ncsu.edu/resources/guidelines/construction-guidelines/>.
 - 2. Thickness: Match Existing .
 - 3. Face Size: Match Existing .
 - 4. Color: Match Existing .
- B. Temporary Protective Coating: Precoat exposed surfaces of brick pavers with a continuous film of a temporary protective coating that is compatible with brick, mortar, and grout products and can be removed without damaging grout or brick. Do not coat unexposed brick surfaces; handle brick to prevent coated surfaces from contacting backs or edges of other units. If, despite these precautions, coating does contact bonding surfaces of brick, remove coating from bonding surfaces before setting brick.

2.2 ACCESSORIES

2.3 AGGREGATE SETTING-BED MATERIALS

- A. Graded Aggregate for Base: Sound, crushed stone or gravel complying with ASTM D2940/D2940M, base material .
- B. Sand for Leveling Course: Sound, sharp, washed, natural sand or crushed stone complying with gradation requirements in ASTM C33/C33M for fine aggregate.
- C. Sand for Joints: Fine, sharp, washed, natural sand or crushed stone with 100 percent passing No. 16 sieve and no more than 10 percent passing No. 200 sieve.
- D. Herbicide: Commercial chemical for weed control, registered with the EPA. Provide in granular, liquid, or wettable powder form.

PART 3 - EXECUTION

3.1 INSTALLATION, GENERAL

- A. Mix pavers from several pallets or cubes, as they are placed, to produce uniform blend of colors and textures.

- B. Cut unit pavers with motor-driven masonry saw equipment to provide clean, sharp, unchipped edges. Cut units to provide pattern indicated and to fit adjoining work neatly. Use full units without cutting where possible. Hammer cutting is not acceptable.
- C. Joint Pattern: Match Existing.
- D. Tolerances: Do not exceed 1/16-inch unit-to-unit offset from flush (lippage) or 1/8 inch in 24 inches and 1/4 inch in 10 feet from level, or indicated slope, for finished surface of paving.
- E. Expansion and Control Joints:
 - 1. Provide for sealant-filled joints at locations and of widths indicated. Provide compressible foam filler as backing for sealant-filled joints unless otherwise indicated; where unfilled joints are indicated, provide temporary filler until paver installation is complete. Install joint filler before setting pavers. Sealant materials and installation are specified in Section 079200 "Joint Sealants."
 - 2. Provide cork joint filler at locations and of widths indicated. Install joint filler before setting pavers. Make top of joint filler flush with top of pavers.
- F. Provide edge restraints as indicated. Install edge restraints before placing unit pavers.

3.2 AGGREGATE SETTING-BED APPLICATIONS

- A. Compact soil subgrade uniformly to at least 95 percent of ASTM D698 laboratory density.
- B. Place aggregate base, compact by tamping with plate vibrator, and screed to depth indicated.
- C. Place drainage geotextile over compacted base course, overlapping ends and edges at least 12 inches.
- D. Place leveling course and screed to a thickness of 1 to 1-1/2 inches, taking care that moisture content remains constant and density is loose and uniform until pavers are set and compacted.
- E. Treat leveling course with herbicide to inhibit growth of grass and weeds.
- F. Set pavers with a minimum joint width of 1/16 inch and a maximum of 1/8 inch, being careful not to disturb leveling base. If pavers have spacer bars, place pavers hand tight against spacer bars. Use string lines to keep straight lines. Fill gaps between units that exceed 3/8 inch with pieces cut to fit from full-size unit pavers.
- G. Vibrate pavers into leveling course with a low-amplitude plate vibrator capable of a 3500- to 5000-lbf compaction force at 80 to 90 Hz. Use vibrator with neoprene mat on face of plate or other means as needed to prevent cracking and chipping of pavers. Perform at least three passes across paving with vibrator.
- H. Spread dry sand and fill joints immediately after vibrating pavers into leveling course. Vibrate pavers and add sand until joints are completely filled, then remove excess sand. Leave a slight surplus of sand on the surface for joint filling.

NCSU Brooks Hall - Phase I Renovations
SCO #22-25338-02A
Bid Documents
in situ studio, inc.

10/24/24

END OF SECTION 321400